

Product Manual (TDS)

PEG(200)DA

Polyethylene glycol (200) diacrylate

CAS 26570-48-9

Characteristics

1. Low odor, low irritation, and low volatility.
2. Low viscosity and high activity, low shrinkage, good flexibility and hydrophobicity.

Application

1. Ink, paint.
2. Diluent.
3. Photoresist.

General characteristics

Appearance: clear and transparent

Chroma (APHA, 25°C): 50 max

Acid value (mg KOH / g): 0.1 max.

Containing water rate (%): 0.1 max.

Viscosity (cps, Brookfield, 25°C) : 10 ~ 18

Proportion (g/cm³, 25°C): 1.070 ~ 1.090

Inhibitor content (ppm): 100 ~ 300

Storage security

Please keep away from the heat source and place it in the shadow.

Store it at normal temperature for 12 months without deterioration.

Please tighten the lid to avoid exposure of light sources and solidifying into gel.

Packaging / Product name

200 kg drum / PEG(200)DA

The information of this product is given in good faith and believed to be reliable. The properties are illustrative only, and are not to be regarded as specifications. The information and/or suggestions are made without warranty since the conditions of the use are beyond our control. Nothing herein shall be construed as a recommendation to use any product in conflict with patents or extending any license under any patents. Buyer must determine the suitability of this product for the intended uses and applications.



抖音号



视频号



公众号