

Product Manual(TDS)

Urethane acrylate BW L855M

Product introduction

BW L855M is a HEMA-free, aliphatic modified urethane acrylate. It features fast curing speed, excellent elasticity and elongation, outstanding leveling and ink wettability, as well as good adhesion to various substrates. It is primarily used in applications such as UV nail polish rubber base coat, adhesives, printing varnish, and related fields.

Product characteristics

Functional	2	Hardness	-
Active Ingredient (%)	100%	Proportion (25°C)	1.05
Appearance (25°C)	Transparent clear liquid	Shrinkage(%)	-
Viscosity (cps at 25°C)	8,000 - 17,000	Refractive Index(nd at 25°C)	1.47
Color (APHA)	≤ 60	Elongation At Break (%)	-
Acid Value (mg KOH/g)	≤ 2	Tensile Strength (MPa)	-

- Excellent elasticity;
- Excellent elongation;
- Good adhesion to various substrates;
- HEMA-free;

Applications

- It is used in LED UV nail polish rubber base coat, UV adhesive, UV printing varnish.

Packaging

- In 20 kg plastic drums
- In 200 kg metal drums

Storage

- Store in a properly sealed container, away from sunlight and heat;
- At normal room temperature storage conditions, the product storage stability of at least 6 months;
- Low temperature or long-term storage, this product may form a false plastic layer;
- This rheological change can be restored by stirring or slight heating (up to 45°C);

It is especially suggested that the above data and suggestions are based on experimental data, but due to the uselessness of users, we can not provide any guarantee for the integrity and accuracy of the information.

We recommend that customers choose our products and adopt them. Determine their applicability before making our recommendations.

